

## PORON® 4790-92 Extra Soft Slow Rebound (Supported)

PROPERTY	TEST METHOD	VALUE		
<b>PHYSICAL</b>				
Density, kg/m <sup>3</sup> (lb./ft <sup>3</sup> )	ASTM D3574-95, Test A	240 (15)	320 (20)	400 (25)
Tolerance		± 10		
Thickness, mm (inches)		1.00 - 3.05 (0.039 - 0.120)	2.06 (0.081)	0.53 - 1.04 (0.021 - 0.041)
Tolerance, %		±10	± 10	± 15
Standard Color (Code)		Black (04)		
Compression Force Deflection, kPa (psi)	0.51 cm/min (0.2"/min Strain Rate Force Measured @ 25% Deflection	2 - 24 (0.3 - 3.5)	7 - 35 (1 - 5)	8 - 58 (1.25 - 8.5)
Typical kPa (psi)		12 (1.7)	22 (3.2)	37 (5.3)
Hardness, Durometer Shore O	ASTM D2240-97	2	-	-
Compression Set, % max	ASTM D1667-90 Test D @ 23°C (73°F)		2	
	ASTM D3574-95 Test D @ 70°C (158°F)		10	
	ASTM D3574-95 Test J/Test D Autoclaved 5 hrs @ 121°C (250°F)		-	
Resilience by Vertical Rebound, %	ASTM D2632-96	4	5	-
<b>ELECTRICAL &amp; THERMAL</b>				
Dielectric Constant, K' ("DK")	ASTM D 150 @ 22°C (72°F) Relative Humidity 50% for 24 hrs		1.48	
Dielectric Strength, volts/mil	ASTM D149-97a		50	
Dissipation Factor, tan D ("DF")	ASTM D150-98		0.04	
Volume Resistivity, ohm-cm	ASTM D257-99		8 x 10 <sup>11</sup>	
Surface Resistivity, ohm/sq.	ASTM D257-99		10x10 <sup>11</sup>	
Thermal Conductivity, W/m-C BTU-in./hr/ft <sup>2</sup> -F)	ASTM C518-98	0.083 (0.53)	-	-
Coefficient of Thermal Expansion		2.3 - 3.1 x 10 <sup>-4</sup> in/in/°C (1.3 - 1.7 x 10 <sup>-4</sup> in/in/°F)		

The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of PORON Polyurethane Foam Materials for each application. The Rogers logo, PORON, and the PORON logo are trademarks of Rogers Corporation or one of its subsidiaries. ©2000-2003, 2006, 2008, 2017, 2019-2021, 2023 Rogers Corporation. All rights reserved. 0723-PDF • Publication #17-039 [www.rogerscorp.com](http://www.rogerscorp.com)

PROPERTY	TEST METHOD	VALUE		
<b>TEMPERATURE RESISTANCE</b>		<b>240 (15)</b>	<b>320 (20)</b>	<b>400 (25)</b>
Recommended Constant Use, max.	SAE J-2236	90°C (194°F)		
Recommended Intermittent Use, max.		121°C (250°F)		
Embrittlement	ASTM D746-98	-20°C (-4°F)	-18°C (0°F)	-12°C (10°F)
Cold Flexibility	MIL-P-12420D 1991 @ -40°C (-40°F)	-		
<b>FLAMMABILITY &amp; OUTGASSING</b>				
Flammability, mm (inches)	UL 94HBF* (File E20305) (Pass ≥)	2.06 (0.081)		
	FMVSS 302 (Pass ≥)	2.06 (0.081)		
	CSA Comp HBR (File 188149) (Pass≥)	2.06 (0.081)		
Fogging	SAE J-1756 3 hrs @ 100°C (212°F)	Pass		
Outgassing, Total Mass Loss (TML) %	ASTM E595-93 24 hrs @ 125°C (257°F) @ <7 x 10 <sup>3</sup> kPa	1.73	1.63	1.44
Outgassing, Collected Volatile Condensable Materials (CVCM) %		0.14	0.29	0.27
Outgassing, Water Vapor Regain (WVR) %		0.71	0.49	0.44
<b>ENVIRONMENTAL</b>				
Gasketing and Sealing	UL JMST2 (Consisting of UL50 & UL508)	-		
	CAN/CSA-C22.2 No. 94-M91	-		
Moisture Absorption, High Humidity Exposure, % Weight Gain, Typical	AMS 3568-95	2		
Water Absorption, Immersion Testing, % Weight Gain, Typical	ASTM D570-95	25	23	14
UV Resistance	ASTM G53-96	-		
Ozone Resistance	GM 4486P-95	-		
Corrosion Resistance	AMS 3568-91	-		
Mildew/Bacteria Resistance	ASTM G21	Good		
Staining	ASTM D925	No Stain		

The data mentioned above represents results of testing the PORON polyurethane foam only. PORON cellular polyurethane materials is supported by being directly cast onto 0.0508 mm (2 mil) polyester film. By casting directly onto the film, a permanent bond is created. Please see physical property data for the film as represented by manufacturer on the next page.

### SUPPORTING MATERIAL-Clear Polyester Film (PET)

PROPERTY	TEST METHOD	VALUE
Coefficient of Friction A/B, (Kinetic)	ASTM D1894	0.40
Density, kg/m <sup>3</sup> (lb./ft <sup>3</sup> )	ASTM D1505	1.395 (87.1)
Modules, MD, kPa (psi)	ASTM D882	3.5 x 10 <sup>6</sup> (5000,000)
Shrinkage, MD, %, (TD)	39 min @ 150°C ( 302°F)	1.2 (0.0)
Tensile Strength, MD, kPa (psi)	ASTM D882	2.1 x 10 <sup>5</sup> (30,000)
Ultimate Elongation	ASTM D882	150
Yield Strength (F5), kPa (psi)	ASTM D882	1.0 x 10 <sup>5</sup> (15,000)

- Notes:
- ‡Designed to meet UL 94 HBF based upon 2022 test criteria. As of 2023 items with nominal density  $\geq 15.6\text{lb/ft}^3$  (250kg/m<sup>3</sup>) are no longer eligible to be tested for UL 94 HBF but remain equivalent.
  - - Represents testing not available at this time.
  - All metric conversions are approximate.
  - Additional technical information is available.
  - Typical values should not be used for specification limits.

To order PORON materials, please contact our Sales Specialists at 860.928.3622 or via email at [EMS\\_CT\\_cust\\_serv@rogerscorporation.com](mailto:EMS_CT_cust_serv@rogerscorporation.com)