



PCB Materials for Handheld Device Antennas

Smartphones | Tablets | Media Players

Increased design flexibility with cost effective solutions

- High dielectric constant options
- Low dielectric loss
- Wide range of dielectric thickness options

Environmentally friendly (RoHS, Lead Free, Halogen Free options)

Global manufacturing and support



RO3000® High Frequency Laminates

Property	Condition & Test Method	
Composition	PTFE-Ceramic Composite	
Dielectric Constant Options, ϵ_r	3.00, 6.15, 10.2	10 GHz, 23°C. IPC-TM-650 2.5.5.5
Dissipation Factor, $\tan \delta$	0.0010 to 0.0022	10 GHz, 23°C. IPC-TM-650 2.5.5.5
Thickness Options	0.005" to 0.250" in 5 mil Increments	
Moisture Absorption	< 0.5%	D-24/23. IPC TM-650 2.6.2.1
Foil Cladding Options	1/2 oz., 1 oz., 2 oz. ED copper, also available unclad	

The information contained in this Sales Sheet is intended to assist you in designing with Rogers' circuit materials. It is not intended to and does not create any warranties; express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the Sell Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' circuit materials for each application.

The Rogers logo and RO3000 are trademarks of Rogers Corporation or one of its subsidiaries. ©2017 Rogers Corporation. All rights reserved.
Printed in USA 0213-PDF AG, Revised 1313 061517 Publication #92-033