

# RO4450T™ Bondply

RO4450T™ 3.2-3.3 Dk, low loss, spread glass reinforced, ceramic filled bonding material is designed to complement RO4835T™ laminates and the existing RO4000® laminate family, and come in multiple thickness options for improved multilayer board design flexibility .

RO4450T bonding materials exhibit excellent Dk control for repeatable electrical performance, a low z-axis expansion for plated through-hole reliability, and are compatible with standard epoxy/glass (FR-4) processes. These materials are an excellent choice for multilayer designs requiring sequential laminations, as fully cured RO4000 products are capable of withstanding multiple lamination cycles. RO4450T bondplys have the UL 94 V-0 flame retardant

rating, and are compatible with lead-free processes. RO4000 bonding materials feature high performance material attributes for outstanding, repeatable wireless performance that provide the optimum blend of price, performance and durability.



## /// Features and Benefits:

Prepreg grades based on RO4000 series core materials

- Compatible in multilayer board constructions with RO4003C, RO4350B, RO4835, RO4350G2, and RO4000 LoPro laminates

Low z-axis coefficient of thermal expansion ranging from 43 to 60 ppm/°C

- CAF resistant

Sequential lamination capable

- High frequency thermoset prepreg compatible with FR-4 bond temperatures

Lead free solder processing compatible

- High reliability plated through-hole

## /// Typical Applications:

- Backhaul Radios
- Communications Systems
- Power Amplifiers
- Small Cells/DAS

Standard Thicknesses	Standard Panel Sizes
0.0025" (0.064mm) +/- 0.0006" 0.0030" (0.076mm) +/- 0.0006" 0.0035" (0.089mm) +/- 0.0006" 0.0040" (0.102mm) +/- 0.0006" 0.0050" (0.127mm) +/- 0.0006" 0.0055" (0.140mm) +/- 0.0006"	16" X 18" (406 X 457 mm) 24" X 18" (610 X 457 mm) 24.5" X 18.5" (622 X 470 mm) 24" X 36" (610 X 915 mm)  *Additional panel sizes available
*Contact Customer Service or Sales Engineering to inquire about additional available product configurations	

### Standard Properties Table

Properties	Typical Values <sup>(1)</sup>						
<b>Electrical Properties</b>							
Thicknesses	2.5 mils (0.064 mm)	3.0 mils (0.076 mm)	3.5 mils (0.089 mm)	4.0 mils (0.102 mm)	4.5 mils (0.114 mm)	5.0 mils (0.127 mm)	6.0 mils (0.152 mm)
Dielectric Constant	3.26 ± 0.05	3.23 ± 0.05	3.19 ± 0.05	3.35 ± 0.05	3.29 ± 0.05	3.28 ± 0.05	3.24 ± 0.05
Dissipation Factor	0.0037	0.0039	0.0033	0.0042	0.0044	0.0038	0.0044
Volume Resistivity	1.1 X10 <sup>9</sup>	2.8 X10 <sup>9</sup>	1.0 X10 <sup>9</sup>	1.4 X10 <sup>9</sup>	7.1 X10 <sup>8</sup>	2.3 X10 <sup>9</sup>	8.9 X10 <sup>8</sup>
Surface Resistivity	7.8 X10 <sup>6</sup>	2.5 X10 <sup>8</sup>	8.3 X10 <sup>6</sup>	1.0 X10 <sup>7</sup>	7.7 X10 <sup>6</sup>	1.7 X10 <sup>8</sup>	6.5 X10 <sup>6</sup>
Electrical Strength (dielectric strength)	1004	1020	972	1040	1070	990	1066
<b>Thermal Properties</b>							
Decomposition Temperature (Td)	397	406	398	408	398	405	397
Glass Transition (Tg)	176	179	188	176	182	177	183
Coefficient of Thermal Expansion	18	20	20	15	17	19	18
Coefficient of Thermal Expansion	18	21	19	16	17	20	18
Coefficient of Thermal Expansion	58	57	63	58	52	62	64
Thermal Conductivity	0.53	0.50	0.51	0.55	0.55	0.53	0.55
<b>Mechanical Properties</b>							
Copper Peel Strength after Thermal Stress	0.79 (4.5)	0.81 (4.6)	0.77 (4.4)	0.77 (4.4)	0.75 (4.3)	0.81 (4.6)	0.79 (4.5)
<b>Physical Properties</b>							
Glass	106	106	106	1078	1078	1078	1078
Resin-Content	79	82	84	75	77	79	83
Color	White	White	White	White	White	White	White
Flammability	V-0	V-0	V-0	V-0	V-0	V-0	V-0
Moisture Absorption	0.05	0.06	0.06	0.05	0.05	0.05	0.06
Lead Free Process Compatible	Yes	Yes	Yes	Yes	Yes	Yes	Yes

<sup>1</sup> Typical values are a representation of an average value for the population of the property. For specification values contact Rogers Corp.

### Standard Properties Table

Properties	Direction	Units	Test Conditions		Test Method
<b>Electrical Properties</b>					
Dielectric Constant	Z	-	23°C @ 50% RH	10 GHz	IPC TM-650 2.5.5.5
Dissipation Factor	Z	-	23°C @ 50% RH	10 GHz	IPC TM-650 2.5.5.5
Volume Resistivity	-	Mohm-cm	C-96/35/90	-	IPC TM-650 2.5.17.1
Surface Resistivity	X,Y	Mohm	C-96/35/90	-	IPC TM-650 2.5.17.1
Electrical Strength (dielectric strength)	Z	V/mil	-	-	IPC TM-650 2.5.6.2
<b>Thermal Properties</b>					
Decomposition Temperature (Td)	-	°C	2hrs @ 105°C	5% Weight Loss	IPC TM-650 2.4.24.6
Glass Transition (Tg)	-	°C TMA	A	-	IPC-TM-650 2.4.24
Coefficient of Thermal Expansion	X	ppm/°C	-	-55°C to 288°C	IPC TM-650 2.4.41
Coefficient of Thermal Expansion	Y	ppm/°C	-	-55°C to 288°C	IPC TM-650 2.4.41
Coefficient of Thermal Expansion	Z	ppm/°C	-	-55°C to 288°C	IPC TM-650 2.4.41
Thermal Conductivity	Z	W/(m-K)	50°C	z direction	ASTM D5470
<b>Mechanical Properties</b>					
Copper Peel Strength after Thermal Stress	X,Y	N/mm (lbs/in)	10s @288°C	35 µm foil	IPC TM-650 2.4.8
<b>Physical Properties</b>					
Glass	-	-	-	-	-
Resin-Content	-	-	-	-	-
Color	-	-	-	-	-
Flammability	-	-	-	C48/23/50 & C168/70	UL 94
Moisture Absorption	-	%	D24/23	-	IPC TM-650 2.6.2.1
Lead Free Process Compatible	-	-	-	-	-

<sup>1</sup> Typical values are a representation of an average value for the population of the property. For specification values contact Rogers Corp.

\\\ 100 S. Roosevelt Avenue \\\ Chandler, AZ 85226 \\\ Tel: 480-961-1382 \\\ Fax: 480-961-4533 \\\ www.rogerscorp.com  
\\\ IPC Slash Sheet # 4103B/540 \\\ UL File # E102763

The information in this data sheet is intended to assist you in designing with Rogers' circuit materials. It is not intended to and does not create any warranties express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on this data sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' circuit materials for each application. These commodities, technology and software are exported from the United States in accordance with the Export Administration regulations. Diversion contrary to U.S. law prohibited.

The Rogers' logo, Helping power, protect, connect our world, RO4000, RO4003C, RO4350B, RO4835, RO4360G2, RO4835T, RO4450T and LoPro are trademarks of Rogers Corporation or one of its subsidiaries.

©2022 Rogers Corporation, Printed in U.S.A., All rights reserved.

Issued 1596 080422 Publication #92-198