

RT/duroid® 5880LZ

High Frequency Laminates

RT/duroid® 5880LZ filled PTFE composites are designed for exacting stripline and microstrip circuit applications.

The unique filler results in a low density, lightweight material for high performance weight sensitive applications.

The very low dielectric constant of RT/duroid 5880LZ laminates is uniform from panel to panel and is constant over a wide frequency range. Its low dissipation factor extends the usefulness of RT/duroid 5880LZ laminates to Ku-band and above.

RT/duroid 5880LZ laminates are easily cut, sheared and machined to shape. They are resistant to all solvents and reagents, hot or cold, normally used in etching printed circuits or in plating edges and holes.

When ordering RT/duroid 5880LZ laminates, it is important to specify dielectric thickness, tolerance, electrodeposited copper foil, and weight of copper foil required.



Features:

- Lowest dielectric constant available
- Low Z-axis CTE
- Lightweight / low density
- Uniform electrical properties over a wide frequency range

Some Typical Applications:

- Airborne antenna system
- Lightweight feed networks
- Military radar systems
- Missile guidance systems
- Point-to-point digital radio antennas

Property	Typical Value [1] RT/duroid® 5880LZ	Direction	Units	Condition	Test Method
Dielectric Constant ϵ_r Process	2.00 ± 0.04	Z		10 GHz/23°C	IPC-TM-650, 2.5.5.5
[2] Dielectric Constant ϵ_r Design	2.00	Z		8 GHz - 40 GHz	Differential Phase Length Method
Dissipation Factor, tan	Typ: 0.0021 Max: 0.0027	Z		10GHz/23°C	IPC-TM-650, 2.5.5.5
Thermal Coefficient of Dielectric Constant, ϵ_r	+20	Z	ppm/°C	-50°C to 150°C 10GHz	IPC-TM-650, 2.5.5.5
Volume Resistivity	1.74 X 10 ⁷		Mohm-cm	C-96/35/90	IPC-TM-650, 2.5.17.1
Surface Resistivity	2.08 X 10 ⁶		Mohm	C-96/35/90	IPC-TM-650, 2.5.17.1
Electrical Strength	40		kV	D48/50	IPC-TM-650, 2.5.6
Dimensional Stability	-0.38	X,Y	%		IPC-TM-650, 2.4.39A
Moisture Absorption	0.31		%	24 hours/23°C	IPC-TM-650, 2.6.2.1
Thermal Conductivity	0.33	Z	W/m/°K	80°C	ASTM C518
Coefficient of Thermal Expansion	54,47 40	X,Y Z	ppm/°C	0 to 150°C	IPC-TM-650, 2.4.41
Outgassing					
	TML 0.01		%		ASTM E-595
	CVCM 0.01				
	WVR 0.01				
Density	1.4		gm/cm ³		ASTM D792
Copper Peel	>4.0		pli		IPC-TM-650, 2.4.8
Flammability	V-O				UL 94
Lead-Free Process Compatible	YES				

- NOTES:
- [1] Typical values are a representation of an average value for the population of the property. For specification values contact Rogers Corporation.
- [2] The Design Dk is an average number from several different tested lots of material and on the most common thickness/s. If more detailed information is required please contact Rogers Corporation or refer to the Design Dk technical articles and presentations available at <http://www.rogerscorp.com>, the Rogers Technology Support Hub.

Standard Thickness	Standard Panel Size	Standard Copper Cladding
0.010" (0.254mm) ± 001 0.020" (0.508mm) ± 001 0.050" (1.270mm) ± 002 0.100" (2.540mm) ± 004	12" X 18" (305mm X 457mm) 24" X 18" (610mm X 457mm) Non-standard panel sizes are available up to 24" X 54" (610mm X 1.37m)	½ oz (18µm) and 1 oz (35µm) Electrodeposited copper foil on both sides

Contact customer service for more information on non-standard and custom thicknesses, claddings and panel sizes.

The information in this data sheet is intended to assist you in designing with Rogers' circuit materials. It is not intended to and does not create any warranties express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on this data sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' circuit materials for each application.

RT/duroid, Helping power, protect, connect our world & the Rogers' logo are trademarks of Rogers Corporation or one of its subsidiaries.
© 2021 Rogers Corporation, Printed in U.S.A., All rights reserved. Revised 1532 100121 **Publication #92-137**