

## DeWAL® DW 750

Pressure sensitive tape produced from a black UHMW polyethylene film with an aggressive acrylic adhesive.

Suitable for chute liners, wear pads, and guide rails. Also suitable for anti-squeak and sound deadening in automotive applications.

- Non-stick surface
- Low friction
- High tensile strength
- Abrasion resistant

PROPERTY	TEST METHOD	750-3	750-5	750-10	750-20
PHYSICAL					
Backing Material		UHMW Film	UHMW Film	UHMW Film	UHMW Film
Backing Thickness, inches, (mm)	ASTM-D374	0.003	0.005	0.010	0.020
		(0.080)	(0.13)	(0.25)	(0.50)
Adhesive System		Acrylic	Acrylic	Acrylic	Acrylic
Adhesive Thickness,	ASTM-D374	0.0023	0.0023	0.0023	0.0023
inches, (mm)		(0.058)	(0.058)	(0.058)	(0.058)
Adhesion Strength to	ASTM-D1000	65	75	75	65
Steel, oz/in, (g/cm)		(725)	(837)	(837)	(725)
	ASTM-D3759/882	20	30	60	120
		(3572)	(5357)	(10715)	(21430)
Elongation,%	ASTM-D3759/882	300	300	300	300
Maximum Operating Temperature, °F, (°C)		200	200	200	200
		(93)	(93)	(93)	(93)
PACKING SPECIFICATIONS					
Maximum Width, inches, (mm)		26	26	26	26
		(660)	(660)	(660)	(660)
Core Diameter, inches, (mm)		3	3	3	3
		(76.2)	(76.2)	(76.2)	(76.2)
Roll Length, yards, (m)		18	18	18	18
		(16.46)	(16.46)	(16.46)	(16.46)
Liner		White Paper	White Paper	White Paper	Blue Poly

All metric conversions are approximate.
Additional technical information is available.
Typical values should not be used for specification limits.

