

PORON[®] 4790-79SE-20 Series-04

Display Back Pad Self-Adhesive

PROPERTY		TEST METHOD		TYPICAL VALUE			
FOAM	PHYSICAL		79SE-20006	79SE-20008	79SE-20012	79SE-20020	
	Density, kg/m ³ (lb./ft ³)	ASTM D3574-95, Test A	320 (20)				
	Tolerance, %		±10				
	Thickness, Foam & FAL, mm (inches)	With digital tester (ONO SOKKI)	0.15	0.20	0.30	0.50	
			(0.006)	(0.008)	(0.012)	(0.020)	
	Tolerance, %	(0110 00144)	± 15	± 15	± 20	± 20	
	Standard Color (Code)		Black (04)				
	Compression Force Deflection, kPa	Modified ASTM D3574	13.8~55.2				
	(psi)	PTP-0033 @ 25% Deflection	(2~8)				
	Peel Adhesion, gf/in	ASTM D1000 82°C (180°F) Peel		≥ 200			
	Shelf Life, months	From date of manufacture		12			

PORON[®] Back Pad materials utilize an acrylic pressure sensitive adhesive manufactured to Rogers' specifications. This adhesive provides reliable bonding to a wide variety of substrates, exhibits high quality optical clarity, withstands a wide range of temperatures and is resistant to chemical exposure.

Notes:

- All metric conversions are approximate.
- Additional technical information is available.
- Typical values should not be used for specification limits.



The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of PORON Polyurethane Foam Materials for each application. The Rogers logo, PORON, and the PORON logo are trademarks of Rogers Corporation or one of its subsidiaries. © 2017, 2019, 2024 Rogers Corporation. All rights reserved. 0624-PDF • Publication #17-364 www.rogers.com