

## PORON<sup>®</sup> 4790-79TS5B-15 Series-04

## **Display Back Pad-Self-Adhesive**

	PROPERTY	TEST METHOD	TYPICAL VALUE
FOAM	PHYSICAL		79TS5B-15 Series
	Density, kg/m³ (lb./ft³)	ASTM D3574-95, Test A	240 (15)
	Tolerance, %		±10
	Thickness, Foam & FAL mm (inches)		0.15~0.41
			(0.006~0.016)
	Tolerance, %		± 15
	Standard Color (Code)		Black (04)
	Compression Force Deflection, kPa (psi)	0.51 cm/min (0.2"/min) Strain Rate	6.89~41.34
		Force measured @ 25% Deflection	(1~6)
	Peel Adhesion, gf/in	ASTM D1000 82°C (180°F) Peel	≥ 200
	Shelf Life, months	From date of manufacture	12

PORON<sup>®</sup> Back Pad materials utilize an acrylic pressure sensitive adhesive manufactured to Rogers' specifications. This adhesive provides reliable bonding to a wide variety of substrates, exhibits high quality optical clarity, withstands a wide range of temperatures and is resistant to chemical exposure.

Notes:

- All metric conversions are approximate.
- Additional technical information is available.
- Typical values should not be used for specification limits.



The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of PORON Polyurethane Foam Materials for each application. The Rogers logo, PORON, and the PORON logo are trademarks of Rogers Corporation or one of its subsidiaries. © 2024 Rogers Corporation. All rights reserved. 0624-PDF • Publication #17-507 www.rogerscorp.com