

PORON® 92 Extra Soft Slow Rebound

PROPERTY	TEST METHOD	VALUE	
PHYSICAL			
Density, kg/m ³ (lb./ft ³)	ASTM D3574-95, Test A	192 (12)	240 (15)
Tolerance, %		± 10	
Thickness, mm (inches)		3.18 - 10.8 (0.125 - 0.425)	3.18 - 12.7 (0.125 - 0.500)
Tolerance, %		± 10	
Standard Color (Code)		Black (04)	
Compression Force Deflection, kPa (psi)	0.51 cm/min (0.2"/min Strain Rate Force Measured @ 25% Deflection	1.7 - 17 (0.25 - 2.5)	2 - 24 (0.3 - 3.5)
Hardness, Durometer Shore OO	ASTM D2240-97	< 3	< 5
Compression Set, % max	ASTM D1667-90 Test D @ 23°C (73°F)	2	
	ASTM D3574-95 Test D @ 70°C (158°F)	10	
	ASTM D3574-95 Test J/Test D Autoclaved 5 hrs @ 121°C (250°F)	5	
Resilience by Vertical Rebound, %	ASTM D2632-96	4	
Dimensional Stability, % max change	22 hrs @ 80°C (176°F) in a Forced-Air Oven	± 3	± 5
Tensile Strength, min. kPa (psi)	ASTM D3574-75 Test E	83 (12)	103 (15)
Tensile Elongation, % min.	ASTM D3574-75 Test E	150	120
Tear Strength, min. kN/m, (pli)	ASTM D264-91 Die C	0.4 (2)	0.53 (3)
ELECTRICAL & THERMAL			
Dielectric Constant, K' ("DK")	ASTM D150 @ 22°C (72°F) Relative Humidity 50% for 24 hrs	-	1.48
Dielectric Strength, volts/mil	ASTM D149-97a	42	50
Dissipation Factor, tan D ("DF")	ASTM D150-98	-	0.04
Volume Resistivity, ohm-cm	ASTM D257-99	-	8 x 10 ¹¹
Surface Resistivity, ohm/sq.	ASTM D257-99	-	10 x 10 ¹¹
Coefficient of Thermal Expansion		2.3 - 3.1 x 10 ⁻⁴ in/in/°C (1.3 - 1.7 x 10 ⁻⁴ in/in/°F)	

The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of PORON Polyurethane Foam Materials for each application. The Rogers logo, PORON, and the PORON logo are trademarks of Rogers Corporation or one of its subsidiaries. © 2000-2003, 2006, 2008, 2009, 2016, 2017, 2020, 2023 Rogers Corporation. All rights reserved. 0723-PDF • Publication #17-038

PROPERTY	TEST METHOD	VALUE	
TEMPERATURE RESISTANCE		192 (12)	240 (15)
Recommended Constant Use, max.	SAE J-2236	90°C (194°F)	
Recommended Intermittent Use, max.		121°C (250°F)	
Embrittlement	ASTM D746-98	-20°C (-4°F)	
FLAMMABILITY & OUTGASSING			
Flammability, mm (inches)	UL 94HBF [†] (File E20305) (Pass ≥)	3.94 (0.155)	3.0 (0.118)
	FMVSS 302 (Pass ≥)	3.94 (0.155)	3.0 (0.118)
	CSA Comp HBF (File 188149) (Pass≥)	3.94 (0.155)	3.0 (0.118)
Fogging	SAE J-1756 3 hrs @ 100°C (212°F)	Pass	
Outgassing, Total Mass Loss (TML) %	ASTM E595-93 24 hrs @ 125°C (257°F) @ <7 x 10 ³ Pa	0.76	1.73
Outgassing, Collected Volatile Condensable Materials (CVCM) %		0.04	0.14
Outgassing, Water Vapor Regain (WVR) %		0.6	0.71
ENVIRONMENTAL			
Gasketing and Sealing	UL JMST2 (Consisting of UL50 & UL508) CAN/CSA-C22.2 No. 94-M91	-	File MH15464
Moisture Absorption, High Humidity Exposure, % Weight Gain, Typical	AMS 3568-95	2	
Water Absorption, Immersion Testing, % Weight Gain, Typical	ASTM D570-95	38	34
Mildew/Bacteria Resistance	ASTM G21	Good	
Staining	ASTM D925	No Stain	

These materials are unsupported and should be processed with the knowledge that stretching of die cut parts can occur when material has not been relaxed.

- Notes:
- †Designed to meet UL 94 HBF based upon 2022 test criteria. As of 2023 items with nominal density ≥ 15.6lb/ft³ (250kg/m³) are no longer eligible to be tested for UL 94 HBF but remain equivalent.
 - Represents testing not available at this time.
 - All metric conversions are approximate.
 - Additional technical information is available.
 - Typical values should not be used for specification limits.