

**PORON® AquaPro® Family: Formulation 37 – Supported – Data Sheet**

PROPERTY	TEST METHOD	VALUE
<b>PHYSICAL</b>		
Density, kg/m <sup>3</sup> (lb. / ft <sup>3</sup> )	ASTM D 3574, Test A	304 (19)
Tolerance, kg/m <sup>3</sup> (lb. / ft <sup>3</sup> )		± 32 (2)
Thickness, mm (in)	ASTM D 3574, Test A	0.50 – 1.0 (0.020 – 0.039)
Tolerance		± 0.10 (.0039)
Compression Force Deflection, kPa (psi)	Modified ASTM D 3574: PTP-0033 at 25% deflection	41 – 110 (6 – 16)
Compression Set, % max. after 24 hour recovery	ASTM D 3574 Test D @ 70°C (158°F)	10
Standard Color (Code)		Black (04)
Recommended Constant Use, Max °C (°F)	SAE J-2236	90 (194)
Recommended Intermittent Use, Max °C (°F)	UL 157	121 (250)
<b>OUTGASSING</b>		
Fogging	SAE J-1756 3 hrs @ 100°C (212°F)	No Fogging
Outgassing, Total Mass Loss (TML) %	ASTM E 595 24 hrs @ 125°C (257°F) @ <7x10 <sup>3</sup> Pa	0.58
Collected Volatile Condensable Materials (CVCM) %		0.02
Water Vapor Regain (WVR) %		0.09
<b>ENVIRONMENTAL</b>		
Moisture Absorption, High Humidity Exposure, % weight	AMS 3568	1.1
Water Immersion, %	ASTM D570	2.84
Water Absorption, Vacuum Exposure, % weight gain	ASTM D 1056	0.94
	ASTM 3568B	0.33

The data mentioned above represents results of testing the PORON polyurethane foam only. PORON cellular polyurethane material is supported by being directly cast onto 2 mil polyester film. By casting directly onto the film, a permanent bond is created. Please see physical property data for the film as represented by manufacturer below.

**Supporting Material – Clear Polyester Film (PET)**

PROPERTY	TEST METHOD	VALUE
Coefficient of Friction A/B, (Kinetic)	ASTM D 1894	0.40
Density, g/cm <sup>3</sup>	ASTM D 1505	1.395
Modulus, MD, psi (kg/cm <sup>2</sup> )	ASTM D 882	500,000 (35,200)
Shrinkage, MD, %, (TD)	39 min. at 150°C	1.2 (0.0)
Tensile Strength, MD, psi (kg/cm <sup>2</sup> )	ASTM D 882	30,000 (2,110)
Ultimate Elongation	ASTM D 882	150
Yield Strength (F5), psi (kg/cm <sup>2</sup> )	ASTM D 882	15,000 (1,050)

Notes:

- All metric conversions are approximate.
- Additional technical information is available.
- Values should not be used for specification limit

The information contained in this Data Sheet is intended to assist you in designing with Rogers’ Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the data sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers’ PORON Polyurethane Foams for each application. The Rogers logo, Helping power, protect, connect our world, AquaPro and PORON are trademarks of Rogers Corporation or one of its subsidiaries. © 2017, 2020 Rogers Corporation, All rights reserved. Printed in U.S.A. 0220-PDF. Publication #17-368