

## DeWAL® DW262 Dynaglide<sup>®</sup> PTFE Materials

DeWAL® DW262 is part of our Dynaglide® family. It is a filled PTFE compounded with glass fibers. DW262 is white in color, and exhibits excellent compressive strength and bearing properties. The thickness range for this product is from 0.25 - 1.14mm (0.010 - 0.045").

• Bearing and seal applications

Applications:

Features & Benefits:

- Non-stick surface, low friction
- Excellent chemical and temperature resistance
- Excellent wear properties

PROPERTY	TEST METHOD	DATA RANGE	TYPICAL VALUE*
PHYSICAL			
Base Film			Glass Filled PTFE
Density, g/cc	ASTM-D 792	2.21 - 2.26	2.24
Tensile Strength, MPa (psi)	ASTM-D 882	12 - 18 (1758 - 2559)	15 (2204)
Elongation, %	ASTM-D 882	125 - 175	150
Dielectric Strength, Volts/mil	ASTM-D 149	150 - 350	250
Maximum Operating Temperature, C° (F°)			260 (500)

PRODUCT DIMENSIONS	METRIC	ENGLISH
Thickness mm, inches	0.25 - 1.14	0.010 - 0.045
Maximum Width mm, inches	12.7 - 305	0.5 - 12
Core Diameter mm, inches	76	3
Maximum Roll OD mm, inches	355	14

\*Typical values shown are from testing at date of manufacture and should not be used for specification limits.

- Additional technical information and product specifications are available upon request.

- Shelf life is 1 year from the date of manufacture with storage conditions of 21°C (70°F) and 50% RH.

- All metric conversions are approximate.



The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers DeWAL products for each application. The Rogers logo, Dynaglide, DeWAL logo and DeWAL are trademarks of Rogers Corporation or one of its subsidiaries. © 2019 Rogers Corporation. All rights reserved. 0919-PDF • Publication #175-163